productinformation

tesa® 4917

Double-sided filmic tape with differential adhesive system

tesa® 4917 consists of a transparent double-sided PP-film with a differential adhesive system. The product can easily be cut with the hot wire systems of common bag machine producers.

Main Application

- Reopenable closure system for filmic bags
- Removable emblems or profiles

Technical Data

Backing material	PP film	Type of liner	PP
Color	transparent	Colour of liner	red
Total thickness	90 μm	Thickness of liner	80 μm
Type of adhesive	tackified acrylic		

Adhesion to

•	Steel (initial)	8.2 N/cm	•	Steel (after 14 days)	11.4 N/cm
	Steel (covered side, initial)	4.5 N/cm		Steel (covered side, after 14 days)	4.1 N/cm
	ABS (initial)	6.9 N/cm		ABS (after 14 days)	10.1 N/cm
	ABS (covered side, initial)	4.2 N/cm		ABS (covered side, after 14 days)	6.0 N/cm
	Aluminium (initial)	7.7 N/cm		Aluminium (after 14 days)	10.2 N/cm
	Aluminium (covered side, initial)	3.5 N/cm		Alu (covered side, after 14 days)	4.7 N/cm
•	PC (initial)	9.0 N/cm		PC (after 14 days)	11.0 N/cm
	PC (covered side, initial)	4.0 N/cm		PC (covered side, after 14 days)	6.8 N/cm
•	PE (initial)	3.9 N/cm		PE (after 14 days)	4.1 N/cm
•	PE (covered side, initial)	1.6 N/cm	•	PE (covered side, after 14 days)	2.3 N/cm
	PET (initial)	6.6 N/cm		PET (after 14 days)	9.3 N/cm
•	PET (covered side, initial)	3.1 N/cm		PET (covered side, after 14 days)	4.7 N/cm
•	PP (initial)	6.4 N/cm	•	PP (after 14 days)	6.9 N/cm
	PP (covered side, initial)	2.7 N/cm		PP (covered side, after 14 days)	2.6 N/cm
•	PS (initial)	7.9 N/cm		PS (after 14 days)	10.0 N/cm
•	PS (covered side, initial)	3.8 N/cm	•	PS (covered side, after 14 days)	5.6 N/cm
•	PVC (initial)	6.5 N/cm		PVC (after 14 days)	11.0 N/cm
	PVC (covered side, initial)	4.0 N/cm		PVC (covered side, after 14 days)	7.0 N/cm

tesa® 4917

Double-sided filmic tape with differential adhesive system

Properties

- Temperature resistance short term
- Temperature resistance long term
- Tack
- Ageing resistance (UV)
- Humidity resistance
- Evaluation across relevant tesa® assortment: ••• very good
- 120 °C
 - C Softener resistance

• • • good

- Jordener resistance
- Static shear resistance at 23°C

Resistance to chemicals

Static shear resistance at 40°C

medium





Additional Information

tesa® 4917 is also available with fingerlift (extended liner) for fast liner removal.

age 2 of 2 - As of 26/07/2018 - en

For latest information on this product please visit http://l.tesa.com/?ip=04917