# productinformation

# tesa® 4957

## 1100 μm double-sided PE foam tape

tesa® 4957 is a double sided PE foam tape for general mounting applications. It consists of a highly conformable PE foam backing and a tackified acrylic adhesive. tesa® 4957 has been externally certified for window bar mounting.

## Product benefits:

- Versatile adhesive for high immediate adhesion on numerous substrates
- Fully outdoor suitable: UV, water and ageing resistant
- Compensates for differing thermal expansion of dissimilar materials
- High immediate bonding strength even at low bonding pressure
- Very good cold shock absorbtion

## Main Application

- POS displays, exhibition sample displays
- Shelf edge labels
- Cable channels, window bars, window skirting trims
- Decorative glass or mirror elements on furniture
- Solar module frames

### Technical Data

	Backing material	PE foam		Type of adhesive	tackified acrylic
•	Color	black/white		Elongation at break	200 %
•	Total thickness	1100 μm	•	Tensile strength	6 N/cm

### Adhesion to

•	Steel (initial)	4.0 N/cm	Steel (after 14 days)	4.0 N/cm
•	ABS (initial)	4.0 N/cm	ABS (after 14 days)	4.0 N/cm
•	Aluminium (initial)	4.0 N/cm	Aluminium (after 14 days)	4.0 N/cm
•	PC (initial)	4.0 N/cm	PC (after 14 days)	4.0 N/cm
•	PE (initial)	1.7 N/cm	PE (after 14 days)	2.2 N/cm
•	PET (initial)	4.0 N/cm	PET (after 14 days)	4.0 N/cm
•	PP (initial)	1.8 N/cm	PP (after 14 days)	3.3 N/cm
•	PS (initial)	4.0 N/cm	PS (after 14 days)	4.0 N/cm
•	PVC (initial)	4.0 N/cm	PVC (after 14 days)	4.0 N/cm

For latest information on this product please visit http://l.tesa.com/?ip=04957

# tesa® 4957

## 1100 µm double-sided PE foam tape

# **Properties**

- Temperature resistance short term
- Temperature resistance long term
- Tack
- Ageing resistance (UV)
- Humidity resistance

- Resistance to chemicals 80°C
  - Softener resistance
  - Static shear resistance at 23°C
  - Static shear resistance at 40°C



Evaluation across relevant tesa® assortment: • • • • very good good medium

80°C

#### Additional Information

#### Liner variants:

- PV0 brown glassine paper (71 μm)
- PV10 red transparent PP film (120 μm)
- PV12 transparent PET (75 μm)
- PV15 blue PE film (100 µm)

#### Peel Adhesion:

- immediately: foam splitting on Steel, Aluminium, ABS, PC, PS, PET, PVC
- after 14 days: foam splitting on Steel, Aluminium, ABS, PC, PS, PET, PVC

tesa® 4957 has been tested and approved by IFT institute for window bar mounting. The test includes UV, driving rain and windload. (IFT report number 509 30742/1).

tesa® 4957 has been tested by TÜV Rheinland, Germany. The test confirms the longterm adhesion performance after IEC 61215 / 61646 climate tests and a 85°C temperature resistance. (TÜV report number 21209595).