# productinformation

# tesa® 4962

# Premium double-sided non-woven tape

tesa® 4962 is a double-sided tape consisting of a non-woven backing and a tackified acrylic adhesive.

tesa® 4962 features especially:

- High adhesion values on different substrates
- Excellent wetting (grabbing) power to rough surfaces
- Excellent temperature resistance performance

# Main Application

Mounting of plastic and foam parts, heavy papers, textile and leather

#### Technical Data

•	Backing material	non-woven		Type of adhesive	tackified acrylic
•	Color	translucent		Elongation at break	3 %
•	Total thickness	160 μm	•	Tensile strength	8 N/cm

#### Adhesion to

Steel (initial)	11.5 N/cm		ABS (after 14 days)	12.0 N/cm
ABS (initial)	11.0 N/cm		Aluminium (after 14 days)	10.5 N/cm
Aluminium (initial)	10.0 N/cm	•	PC (after 14 days)	12.4 N/cm
PC (initial)	13.0 N/cm	•	PC (covered side, after 14 days)	14.0 N/cm
PE (initial)	6.5 N/cm	•	PE (after 14 days)	7.0 N/cm
PET (initial)	9.5 N/cm	•	PET (after 14 days)	10.5 N/cm
PP (initial)	8.5 N/cm	•	PP (after 14 days)	10.0 N/cm
PS (initial)	12.0 N/cm	•	PS (after 14 days)	13.0 N/cm
PVC (initial)	11.0 N/cm	•	PVC (after 14 days)	15.0 N/cm
Steel (after 14 days)	12.0 N/cm			

# **Properties**

Temperature resistance short term	200 °C	<ul> <li>Resistance to chemicals</li> </ul>	•••
Temperature resistance long term	80 °C	<ul> <li>Softener resistance</li> </ul>	• •
Tack	• • • •	<ul> <li>Static shear resistance at 23°C</li> </ul>	• • •
Ageing resistance (UV)	• • • •	<ul> <li>Static shear resistance at 40°C</li> </ul>	• •
Humidity resistance	•••		

Evaluation across relevant tesa® assortment: •••• very good ••• good •• medium • low

tesa\*

For latest information on this product please visit <a href="http://l.tesa.com/?ip=04962">http://l.tesa.com/?ip=04962</a>

# tesa® 4962

# Premium double-sided non-woven tape

# Additional Information

Liner variants:

PV0 brown glassine paper (71 μm)

According to VDA278 analysis, tesa 4962 does not contain any single substances restricted by the drafted GB regulations (China) as well as the indoor concentration guideline by Health, Labour and Welfare Ministry (Japan).

Page 2 of 2 - As of 26/07/2018 - i

For latest information on this product please visit <a href="http://l.tesa.com/?ip=04962">http://l.tesa.com/?ip=04962</a>